

Commercial Alumina

Product Overview

Moderate particle size, good fluidity, light flying, easy to dissolve, strong fluorine absorption, low content of impurity elements.

Main Uses of The Product

- (1) Electrolytic Aluminum (2) Calcinated Alumina Raw Materials
- (3) Ceramics (4) Glaze (5) Corundum Raw Materials
- (6) Pure Calcium Aluminate Cement (7) Glass Industry

Product Characteristic Index

Product Model	Chemical Composition (%)					Loss on Lgnition (%)	Specific surface area (m2/g)	-45μm Content(%)	Water content
	Al2O3	SiO2	Fe2O3	Na2O	CaO				
AO-1	≥98.60	≤0.020	≤0.020	≤0.45	≤0.03	≤1.0	≥60	≤20	—
Corundum is suitable for AO	≥98.60	≤0.018	≤0.015	≤0.28	≤0.45	≤1.0	≥60	≤20	—
Screening Alumina	≥98.60	≤0.040	≤0.020	≤0.50	—	—	—	—	< 2
Finely Matched Alumina	≥98.50	—	≤0.020	≤0.75	—	≤1.0	—	—	—