

Ultra-low Sodium Calcined α Alumina For Special GLass (Coarse Powder)

Product Characteristic Index

Product Model	Chemical Composition (%)				Loss on Ignition (%) (\leq)	Effective density (g/cm ³) (\geq)	α -Al ₂ O ₃ (%) (\geq)	Original grain size (μ m)	Coarse powder size (μ m)
	Al ₂ O ₃ (\geq)	SiO ₂ (\leq)	Fe ₂ O ₃ (\leq)	Na ₂ O (\leq)					
AC-05GS	99.7	0.05	0.02	0.03	0.1	3.93	93	2-3	70 \pm 10
AC-102	99.7	0.05	0.02	0.03	0.1	3.93	93	1 \pm 0.5	80 \pm 10